

## AMFORM 200

**Amform is an uncured silicone rubber compound**

Amform cures under standard composite curing conditions (120°C), allowing easy production of permanent formers / intensifiers. Amform can be processed during the initial curing of the first component improving pressure in difficult to form corners. Amform can also be used as a semi-rigid inner mould allowing consistent finishes in the inside of composite components.

### CHARACTERISTICS

- ◆ Cures 1hr at 120°C.
- ◆ Low shrinkage (approx 2%)
- ◆ High end use temperature (200°C).
- ◆ Good chemical resistance.
- ◆ Initial self release properties
- ◆ Ease of use – single component (no mixing).

---

#### Supplied by:

Amber Composites Ltd 94 Station Road  
Langley Mill Nottingham NG16 4BP  
Tel: 01773 530899 Fax: 01773 768687

Issue Ref: PDS/Amform200/02

Issue Date: Nov 07

## **PACKAGING**

Standard Pack size: 5Kg (6.00mm nominal thickness)

Refrigerated storage life is at least 6 months (5°C).

## **HANDLING SAFETY**

Observe established precautions for handling chemicals - wear gloves.

For further information refer to Safety Data Sheet.

## **FURTHER INFORMATION - PROCESSING DETAILS**

Please contact our Technical Sales Engineer for further details.

This is not a specification. The information given in this data sheet in relation to the performance, storage and other characteristics of the product is based on results gained from experience and tests and is believed to be accurate. Given, however, that conditions of use and storage will vary, Amber Composites will not be liable for any loss or damage resulting from reliance upon such information. The purchaser is recommended to carry out his own tests to establish the suitability of the product for its particular purpose. The use of the product in certain processes may require third party consent.